

# RZ-5341

## Epoxy Phenolic Coating

### Product Description

RZ-5341 is a two component, amine cured, high performance modified epoxy phenolic coating.

### Recommended Use

As a protective coating for tanks lining and steel structures to be immersed or exposed to splash or spillage of sea or potable water, solvents and chemicals. It is used as a primer and topcoat for insulated and uninsulated external stainless steel surfaces including equipment and pipe work operating to 200°C. It can be used as final coat in carbon steel surfaces.

### Outstanding Characteristics

- Excellent oil resistance
- Excellent chemical resistance against weak acids, alkalis and solvents
- Good Adhesion to galvanized and stainless steel surfaces.
- Suitable for immersion in warm water
- Corrosion resistance in moderately to severely environment
- Good compatibility with cathodic protection.

### Surface Preparation

The surface must be clean and dry. All dirt, grease, mill-scales and any other foreign materials should be removed. Old primed surfaces must be roughened.

\*A completely clean surface is mandatory to ensure intercoat adhesion, especially at long recoating intervals, any dirt, oil, and grease has to be removed, e.g. with suitable detergent. All of the salt to be removed by fresh water hosing. To check an adequate quality of the surface cleaning a test patch is recommended before recoating.

### Technical Data

Finish	Flat-Semi flat
Color	White, Grey
Volume Solids	58 ± 2%
Specific Gravity	1.4 ± 0.05 gr/cm <sup>3</sup>
Flash Point	26 °C
Dry Film Thickness	100 -150 microns
Theoretical Coverage	5.8 - 3.86 m <sup>2</sup> /lit 4.14 - 2.76 m <sup>2</sup> /kg
Touch dry	4 hrs at 25 °C
Fully cured	7 days at 25 °C
Thermal Resistance	Continuously 180 °C Short time: 220°C
Shelf life	12 months at 25 °C

### Application Details

Application method	Air/Airless spray , Brush, Roller
Nozzle orifice	0.017"-0.023"
Nozzle pressure	200 bar / 2900 Psi
Ambient temperature	10-45° C
Mixing ratio	Base / Hardener 4 / 1 by weight
Thinner/Cleaner	RZT- 51
Pot life	90 minutes at 25°C

Recoat interval min: 12 hrs at 25°C  
Recoat interval max: 5 days at 25°C

\*overcoating times will reduce significantly at high ambient temperature or in strong sunlight.

Revised  
NOV 2017

## Application Procedure of RZ-5341

1. Flush all equipment with recommended cleaner before use.
2. Stir pigmented resin (in the larger container) to an even consistency with a power mixer.
3. Add cure to pigmented resin, and continue stirring for 5 minutes.

**Note:** Since the pot life is limited and shortened by high temperatures, do not mix more material than will be used in 90 minutes at 25°C.

4. For conventional spray, thin with no more than 10-15% of recommended thinner for workability. For airless spray 5-10% of thinner is normally sufficient.
  5. Stir during application to maintain uniformity of material. Apply a wet coat by parallel passes. Overlap each pass 50% to avoid bare areas, pinholes or holidays.
  6. Double coat all welds, rough spots, sharp edges, rivets, bolts, etc. to ensure proper thickness.
  7. Check thickness of dry coating with a non-destructive dry film thickness gauge. Recoat if greater thickness is required.
- Note:** If the maximum recoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.
8. Random pinholes, holidays and small damaged or bare areas can be touched up by brush when the film is dry to touch. Larger areas should be sprayed.
  9. In confined areas ventilate with clean air during application and drying until all solvents are removed.
  10. Clean all equipment with recommended cleaner immediately after use.

## Environmental Conditions

Surface temperature must be at least 3°C above dew point. Relative humidity during application should be less than 80%. Do not apply coatings under reverse environmental conditions.

Each coat shall be air dried a minimum of 12 hours at 25°C prior to recoating. Longer recoat times will be required at lower temperatures. Normal recoat time is within 12 hours. Longer recoat times may require special surface preparation. These coating shall not be applied at temperatures below 10°C.

## Safety

This product is flammable. Keep away from heat and open flame. Keep container closed. Avoid prolonged and repeated contact with skin.

Since improper use and handling can be hazardous to health and cause fire or explosion, safety precautions included with application instructions must be observed during all storage, handling, and use and drying periods.

If used in confined areas:

- circulate adequate fresh air continuously during application and drying.
- Use fresh air masks and explosion proof equipment
- Prohibit all flames, sparks, welding and smoking
- Take precautionary measures against static discharges

Keep away from food products.

## Storage conditions

Store in cool dry conditions, away from sources of heat and naked flames, in the original, unopened packs. If stored at high temperature, the shelf life may be reduced.

## Disclaimers

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience.

However we reserve the right to change the given data without notice.

Any recommendation relating to the use of the products is based on data believed to be reliable. It is buyer to satisfy itself of the suitability of the product for its own particular use.

As the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself.

# RANGIN ZEREH

## High Performance Protective Coatings

No.15- 15<sup>th</sup> St. Bokharest Ave. Tehran/ Iran  
 Tel: +98 21 88723676 Fax: +98 21 88716358  
<http://www.Rsnginzereh.com>  
 Email: info@Ranginzereh.com

Revised  
 NOV 2017